



RED X PRO

RED BLOCKER

**SPECIFICATIONS:**

VOC.....	<275 g/L
Solids.....	12%
Flash Point.....	>200°
Solvent	Water/Glycol Ether
Viscosity.....	500 cps
Odor	Mild, Non Objectionable
Coverage	400 - 500 sq. ft/gal
Dry Time.....	2 - 3 Hours
Cure Time	Full Cure In 72 Hours
Color (Wet).....	Greenish
Color (Dry).....	Light Tan
Gloss Level (60%)	N/A
Sheens.....	N/A
Sizes	1g Container

FEATURES

- Blocks Red/Pink Tones In Red Oak
- One Coat, Easy To Use Waterbased Formula
- Quick Drying, Low Odor & Stainable With Pastel Colors

ONE-STEP METHOD TO CAPTURE THE WHITE OAK FLOORING LOOK

Absco Red X Pro Red Blocker is a one-step waterborne formula designed to block the red and pink tones in red oak giving it the look of a raw white oak floor. Red X Pro is not a bleach, but a low odor, quick drying water-based formula that can be used as a blocker to help achieve lighter wood tones without red and is compatible with all Absco products.

Please refer to the product label for specific surface preparation and application instructions.



THIS IS **CANLAK COATINGS**

To find out more about our innovative line of coatings, visit canlakcoatings.com or call us at **800-432-4333**.



RED X PRO

RED BLOCKER

Absco Red X Pro Red Blocker is a one-step waterborne formula designed to block the red and pink tones in red oak giving it the look of a raw white oak floor. Red X Pro is not a bleach, but a low odor, quick drying water-based formula that can be used as a blocker to help achieve lighter wood tones with out red and is compatible with all Absco products.

SURFACE PREPARATION: Proper surface preparation is essential to achieve a high-quality finish. Sand floors according to NWFA / NOFMA standards for a stained floor.

INSTRUCTIONS: On raw finish sanded wood, apply Red X Pro with a 3/8 inch microfiber roller or a lightweight T-bar @ 400 - 450 sf/gal. Allow to dry 2 - 3 hrs. DO NOT water pop before applying Red X Pro. Only ONE COAT of Red X Pro is needed. A second coat will result in a light green floor.

NATURAL: Do not abrade the coat of Red X Pro. For a light natural look, apply 1 coat of a clear water-based finish such as Absco Solo Pro, Grand Clear 1K or Platinum 2K directly over Red X Pro. Abrade the 1st finish coat with a 180 or 220 sanding strip. Apply additional finish coats as needed.

STAIN: Only pastel colors such as grays, whites and beiges will work properly. Always do a test area. When staining over Red X Pro it is important to follow the following steps: **1.** Be sure to apply Red X Pro evenly in the room as well as the whole project. **2.** When applying stain over Red X Pro, be sure to clean up all residual stain. We recommend buffing with a clean carpet pad or terry cloth bonnet. **3.** Allow stain to dry thoroughly (24 hours If needed). **4.** When the stain has dried, buff the floor evenly with a maroon pad while being cautious not to buff through to bare wood. **5.** Vacuum and tack floor. **6.** Apply 1 coat of a clear water-based finish such as Absco Solo Pro, Grand Clear 1K or Platinum 2K directly over Red X Pro. Abrade the 1st finish coat with a 180 or 220 sanding strip. Apply additional finish coats as needed.

APPLICATION: When applying Absco products over a stain, make sure that the stain has dried properly. Check the directions on the stain package, as different brands will have different drying times. Most oil-based stains would require a minimum of 24 hours before top coating.

DRYING TIME: When applied according to directions, Red X Pro should be dry in 2 - 3 hours. Heavy application, high humidity, or lack of air flow will extend drying times.

COVERAGE: 400 - 450 sq. feet per gallon.

CLEAN-UP: Use warm water to clean brushes and applicators. Dispose of applicators properly. NEVER reuse an applicator to avoid cross contamination. Wash hand with warm water when completed.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

FACTORS BEYOND OUR CONTROL PREVENT US FROM ASSUMING RESPONSIBILITY FOR DAMAGE TO PROPERTY OR PERSON, EVEN WHEN THIS PRODUCT IS APPLIED ACCORDING TO DIRECTIONS. IN NO EVENT SHALL OUR LIABILITY EXCEED THE PURCHASE PRICE HEREOF.

THIS PRODUCT HAS A MAXIMUM VOC OF 275 g/L. FOR WOOD SUBSTRATES ONLY.

Item Number	Description	Size	Number per Case	Weight per Case
31001	Absco Red X Pro Red Blocker	GL	4	38 lbs.



THIS IS **CANLAK COATINGS**

To find out more about our innovative line of coatings, visit canlakcoatings.com or call us at **800-432-4333**.